# WeaversWorld RANGE NAME:

#### PLEASE NOTE: Due to monitor differences, actual colours may vary from what appears online.



PLEASE NOTE: Due to monitor differences, actual colours may vary from what appears online.

| Skye     | 57 | Dusk      | 40   | Wasabi       | 49   | Salt       | 55   |
|----------|----|-----------|------|--------------|------|------------|------|
| Airforce | 51 | Peacock   | 59   | Mamba        | 47   | Blonde     | 21   |
| Bahama   | 26 | Dive      | 3012 | Pesto        | 46   | Fennel     | 60   |
| Cobalt   | 50 | Antarctic | 3013 | Lime         | 9    | Tendril    | 3006 |
| Hyacinth | 2  | Atlantis  | 3011 | Sage         | 29   | Eucalyptus | 3009 |
| Sapphire | 58 | Midnight  | 6    | New Englance | 3008 | Woodland   | 4    |

**<u>PLEASE NOTE</u>**: Due to monitor differences, actual colours may vary from what appears online.



**PLEASE NOTE**: Due to monitor differences, actual colours may vary from what appears online.



## **RANGE NAME:** WeaversWorld ARAGON

**PLEASE NOTE**: Due to monitor differences, actual colours may vary from what appears online.

| APPLICATION:    | UPHOLSTERY & SCREENING                     |
|-----------------|--|
| COMPOSITION:    | 100%                                       |
| PES WIDTH:      | 142cm                                      |
| MASS:           | 310 gm/1m                                  |
| PATTERN REPEAT: | PLAIN                                      |
| COMPLIES WITH:  | SABS 1324 OFFICE PARTITIONS SPECIFICATION. |

### COLOUR FASTNESS:

|                      |      | STD         | ARAGON       |
|----------------------|------|-------------|--------------|
| ABRASION RESISTANCE: |      | 25,000 RUBS | +25,000 RUBS |
| TO LIGHT:            |      | 4           | 4            |
| TO RUBBING:          |      | 4           | 4            |
| PILLING:             |      | 4           | 4            |
| SEAM SLIPPAGE:       | WARP | 180N        | 180N         |
| TENSILE STRENGTH:    | WARP | 400N        | 400N         |





### **RANGE NAME:** WeaversWorld OMNIA

**PLEASE NOTE**: Due to monitor differences, actual colours may vary from what appears online.

| APPLICATION:    | UPHOLSTERY & SCREENING                     |
|-----------------|--|
| COMPOSITION:    | 100% PES                                   |
| PES WIDTH:      | 142cm                                      |
| MASS:           | 346 gm/1m                                  |
| PATTERN REPEAT: | PLAIN                                      |
| COMPLIES WITH:  | SABS 1324 OFFICE PARTITIONS SPECIFICATION. |

### COLOUR FASTNESS:

|                     |      | STD         | OMNIA        |
|---------------------|------|-------------|--------------|
| ABRASION RESISTANCE |      | 25,000 RUBS | +45,000 RUBS |
| TO LIGHT:           |      | 5           | 5            |
| TO RUBBING:         |      | 4-5         | 4-5          |
| TO DRY CLEANING:    |      | 4           | 4            |
| TO PERSPIRATION:    |      | 4           | 4            |
| PILLING:            |      | 4-5         | 4-5          |
| SEAM SLIPPAGE:      | WARP | 180N        | 180N         |
|                     | WEFT | 180N        | 180N         |
| TENSILE STRENGTH:   | WARP | 400N        | 1500N        |
|                     | WEFT | 400N        | 1055N        |





### RANGE NAME: SUPALETHA BONDED LEATHER

**PLEASE NOTE**: Due to monitor differences, actual colours may vary from what appears online.

APPLICATION:UPHOLSTERY & SCREENINGPES WIDTH:140cmPATTERN REPEAT:PLAIN

COMPLIES WITH: ATS Test and SABS 2532/L1/IL75

#### COLOUR FASTNESS:

| TEST                       | ATS<br>TEST METHOD  | SPECIFICATION |          | TEST RESULTS              |       |
|----------------------------|---------------------|---------------|----------|---------------------------|-------|
| TEST                       |                     | WARP          | WEFT     | WARP                      | WEFT  |
| ABRASION RESISTANCE        | EN ISO 12947-2:1998 | >250 000 Revs |          | 770 N                     | 700 N |
| TENSILE STRENGTH           | EN ISO 13934-2:1999 | 720 N/in      | 650 N/in | 70 N                      | 80 N  |
| TEAR STRENGTH              | EN ISO 1397-3:2000  | 35 N          | 40 N     | 31 N                      | 49 N  |
| PEALING STRENGTH           | EN ISO 2411:2000    | 30 N          | 25 N     | 447 N                     | 408 N |
| SEAM STRENGTH              | EN ISO 13936-2:2004 | ≥ 200 N       |          | N                         | N     |
|                            |                     |               |          |                           |       |
| COLOUR FASTNESS TO RUBBING | EN ISO 105-X12:2002 | 5             |          | Dry:                      | 5     |
|                            |                     | 5             |          | Wet:                      | 5     |
| COLOUR FASTNESS TO LIGHT   | EN ISO 105-B02      | ≥ 4           |          | Passed (6)                |       |
| FLEXING RESISTEANCE        | EN ISO 32 100       | 100 000 Revs  |          | No Cracks/No Delamination |       |
| BALLY TEST AFTER HYDROYSIS | EN ISO 32100        | 15 000 Revs   |          | No Cracks/No Delamination |       |
|                            |                     |               |          |                           |       |







**PLEASE NOTE**: Due to monitor differences, actual colours may vary from what appears online.